



# CHEMRAZ® 555

## Broad Chemical Resistance at Elevated Temperatures

### SUPERIOR COMPRESSION SET RESISTANCE


With its broad chemical resistance, Chemraz® 555, a perfluoroelastomer, is ideally suited for challenging fluid handling applications. Chemraz 555 provides a significantly wider operational band and superior compression set resistance than any other broad range perfluoroelastomer on the market. With an upper temperature limit of 600°F (316°C), it is the elastomer of choice for the most demanding services found in the chemical process and refining industries.

Chemraz 555 is suitable for use in a wide variety of media including acids, caustics, aldehydes, esters, ethers, aromatics, hot water, steam, amines, methanol, ketones, TBA, MTBE and mixed process streams. Chemraz 555 is one of Greene, Tweed's many cost-effective products and services that extend the reliability and life of our customers' equipment in hostile conditions while protecting people and the environment from unwanted emissions.

Chemraz 555 is available in O-rings, gaskets and many other custom shapes.

### FEATURES & BENEFITS

- Superior high temperature capability (600°F/316°C) combined with broad chemical resistance in a wide range of media
- Outstanding physical properties allows for robust designs in various applications
- Excellent compression set maintains seal integrity in wide temperature and pressure variations as well as vibration
- Breadth of service capabilities can reduce the number of products in inventory through seal standardization
- Longer and better seal integrity in seal applications lowering life cycle cost of the equipment



### APPLICATIONS


- Mechanical seals
- Valves
- Pump housings
- Sampling/metering equipment
- Reactors
- Quick connect couplings
- Mixers
- Controls/instrumentation
- Compressors
- Sprayers/dispensers

### TYPICAL PROPERTIES\*

Physical Properties	ASTM Method	Typical Value
Color		Black
Specific Gravity	D792	2.00
Hardness, Type A, Points	D2240	80
<b>Mechanical</b>		
Compression Set, 22 hours @ 400°F (204°C) @ 25% Deflection, %	D395	20
Elongation @ Break, %	D1414	175
Modulus @ 50% Elongation, psi (MPa)	D1414	450 (3.1)
Modulus @ 100% Elongation, psi (MPa)	D1414	1,480 (10)
Tensile Strength @ Break, psi (MPa)	D1414	3,430 (24)
<b>Thermal</b>		
Service Temperature Range, °F (°C)		10°F to 600°F (-12°C to 316°C)

\* Note: Unless otherwise indicated, all tests are performed on (-214) O-rings. All test results are preliminary.

The following chart compares compression set resistance of Chemraz® 555 and several other materials currently on the market.



■ Contact Us

Greene, Tweed  
Energy  
1930 Rankin Road  
Houston, TX, USA

Tel: +1.281.765.4500  
Tel: +1.800.927.3301  
Fax: +1.281.821.2696

*Statements and recommendations in this publication are based on our experience and knowledge of typical applications of this product and shall not constitute a guarantee of performance nor modify or alter our standard warranty applicable to such products.*